

BARITAINERS® CHEMICAL RESISTANCE TABLE

E = Excellent

G = Good

Acetic Acid	G	Ink	E
Acetone	E	Isopropanol	E
Benzene	E	Ketones	E
Brake Fluid	G	Linseed Oil	E
Butane	E	Lubrication Oil	E
Chlorobenzene	E	Methane	E
Chloroethoxyethylene	E	Methanol	G
Chloroethoxymethane	E	Methyl Ethyl Ketone	E
Citrus Oil	E	Methyl Glycol	G
Cyclohexane	E	Monochloroethyl Acetate	E
Cyclohexanol	E	Monochloromethyl Acetate	E
Cyclohexanone	E	Naphthalene	E
Dichlorobenzene	G	Nitrobenzene	E
Dichloroethane	G	Paint Solvents	E
Dichlorofluoromethane	E	Palm Oils	G
Dichlorotetrafluoroethane	E	Parafin Oil	G
Dioxan	E	Paraxylene	G
Edible Fats & Oils	E	Phenol	E
Ethanol	E	Polyglycols	E
Fats & Waxes, edible	E	Propanol	G
Fatty Acids	E	Pyridine	E
Fatty Alcohols	E	Shellsol A/AB	E
Fruit Juices	E	Silicone Oils	E
Fuel, Diesel	E	Solvesso 100/150	E
Fuel, Gasoline	E	Sulfolane	G
Gear Oil	E	Terpenes	E
Glycerol	E	Tetralin	E
Grease	E	Thinner	G
Heptane	E	Toulene	E
Hexachloroethane	E	Trichloroethylene	E
Hexachlorobenzene	E	Trichlorotrifluoroethane	E
Hexane	E	Triethanolamine	E
Hydraulic Fluid	E	Turpentine	G
Hydraulic Oil	G	Xylene	E

Data are based on a concentration of 4% Quoral® BR and testing at 25°C. We recommend that users perform specific tests and comply with applicable laws and regulations.

Dynalon
Labware
quality . value . service

For additional information contact Dynalon at 1.800.334.7585 or www.dynalon.com